



Miracote MPC Park Deck

Product Technical Data Sheet

MPC Park Deck Coating is a two-component, polymer modified, cementitious coating for the waterproofing and protection of concrete parking deck surfaces. It consists of a unique rubber-like polymer liquid which is mixed with a proprietary cement and aggregate blend. MPC Park Deck Coating is typically applied by notched squeegee and back-rolled, but can also be easily applied by hand trowels, magic trowels, brush or spray.

Designed for either exterior or interior use, MPC Park Deck Coating restores and protects concrete surfaces from the consequences of exposure to water intrusion, chlorides, freeze thaw damage, carbonation and the impact and abrasion of vehicular traffic. MPC Park Deck Coating is an extremely durable, cost-effective “breathable” traffic deck coating that allows for the transmission of inherent moisture vapor within concrete without blistering or delamination. This unique benefit helps reduce internal moisture content which can contribute to significant reductions in corrosion rates of steel reinforcement.

MPC Park Deck Coating is available in two aggregate blends depending on the volume and severity of traffic conditions. Miracote MPC Regular Powder is ideal for normal conditions in parking stalls, drive lanes and turn lanes. MPC Hard Powder with aluminum oxide aggregate provides enhanced abrasion resistance where more extreme duty is required, such as in turn lanes, entrance and exit ramps or other high traffic volume areas.

For detailing and treatment of existing cracks, MiraFlex Membrane A is an elastomeric rubber emulsion that is required to use for crack isolation. For enhanced cleanability and stain resistance, consult with Crossfield Products for appropriate clear acrylic, polyurethane or siloxane-based surface sealers.

ADVANTAGES

- Moisture vapor permeable – reduces potential for corrosion
- Protects against ingress of water, chlorides and carbonation
- Ideal for exterior/interior, pedestrian and vehicular traffic
- Excellent adhesion to damp concrete substrates
- Lower labor and material costs
- Reduce life cycle cost – extend service life of parking decks
- One product for all three coats
- No broadcasting or recovery excess sand
- Less sensitivity in adverse weather conditions
- No odor – VOC and LEED compliant

COVERAGE RATES

Theoretical coverage per unit:

Two Coat Application	250 sq. ft. @ 1/16” (62.50 mils)
Three Coat Application	166 sq. ft. @ 3/32” (93.75 mils)
Approximate Yield/Unit	1.25 cu. ft. (tech dept to verify)

Actual consumption rates are dependent on many factors including, but not limited to, substrate texture and porosity, variations in applied thickness and normal allowance for waste.

PACKAGING and COLORS

MPC Liquid Catalyst Component (5 gallon pail)

MPC Regular Powder, Natural Gray or White* (55 lb bag)

*To match Standard Colors requires use of White Powder

MPC Regular Powder, Gray & White Blend (55 lb bag)

MPC Hard Regular Powder, Natural Gray or White (55 lb bag)

MIX RATIO

5 Gal Liquid Catalyst: 2 Bags of MPC Powder

SHELF LIFE AND STORAGE

One year from the date of manufacture as long as containers remain unopened and material is stored in a protected environment free from moisture, excessive heat, freezing temperatures, and direct sunlight.

WHERE TO USE

- Parking Deck Waterproofing & Protection
- Restoration and protection for stadiums and sports arenas
- Waterproofing protection for plaza decks
- Ideal for concrete slabs on metal pans (unvented)

TYPICAL PHYSICAL PROPERTIES @ 75°F (24°C)

Working Life	15-60 minutes (temperature dependent)
Recoat Time	1-4 hours or when dry
Open to Traffic	12 – 24 hours
Adhesion ASTM C882, Type 1.....	515 psi
Tensile Strength ASTM C190.....	450 psi
Compressive Strength ASTM C109.....	2,440 psi
Water Vapor Permeability ASTM E96.....	1.96 perms/in
Water Absorption Weight gain of 4” coated concrete cube after 21 days water immersion.....	<2%
Canadian Mortgage/Housing Corp.....	8.79%
ME 8211-09230 (2” CUBE, IMMERSION @ 48 hrs)	
Freeze-Thaw Resistance – 50 Cycles	no scaling/peeling/flaking (Concrete cylinders immersed for 8 hrs in coated salt water solution followed by 16 hrs. of freezing).
Weathering ASTM G23	No visible degradation (Method I Procedure, 60 cycles)
Resistance to Wind Driven Rain Fed Spec. TT-C-558.....	(8hrs)
Fed. Spec TT-C-0035	(24hrs)
At 5” water pressure and 60 gal/hr water flow, no water or dampness noted on back of test panels.	
Resistance to Hydrocarbon Substances	ASTM D1308 (Spot Open Test) No softening or attack – after 21 days repeated re-application of gasoline, SAE-10 motor oil and jet fuel.
Impact Resistance MIL-D-3134, Para.4.7.3	2 lb steel ball dropped from 8’ height onto coated steel plate
	No cracking or detachment
Flammable Properties ASTM E84	Flame spread – 4 Smoke Density – 0
Fire Resistance UL790.....	Complies as Class A
Potable Water Compatibility	NSF/ANSI Compliant

FOR BEST RESULTS

- Always install a minimum 4’ by 4’ test area or job site mock up for owner approval of acceptable color, texture, finish adhesion and any other critical requirements prior to proceeding with the installation.
- Verify that the most current versions of product technical data sheets (PTDS), material safety data sheets (MSDS), and installation guidelines (IG) are being utilized for project submittals and application reference.

Miracote MPC Park Deck

Product Technical Data Sheet

FOR BEST RESULTS (Continued)

- Protect materials at all times from excessive heat and cold.
- Regularly check wet film thickness with mil gauge and monitor product consumption to ensure correct application thicknesses are obtained.
- The proper application of this product is the sole responsibility of the end user. Job site visits by Miracote representatives are only for the purpose of making recommendations. Supervision and quality control are the sole responsibility of the user.
- Measure surface and ambient temperatures to ensure that material is only applied when temperatures are 40 F (4.5 C) and rising during placement and cure time.
- As with concrete and other cementitious or masonry products, surface staining and tire marking may occur. Apply a clear film-forming or penetrating sealer to enhance stain resistance, cleanability and minimize tire marking.
- Natural gray and pigmented cementitious coatings may exhibit color variegation due to fluctuating evaporation rates during cure. For better color consistency, apply a topcoat of MiraGard Colorbond or other Miracote pigmented topcoats.

OVERVIEW OF INSTALLATION STEPS

• Surface Preparation

All surfaces to be coated must be clean, sound and free from any bond inhibiting substances including, but not limited to, grease, oil and any other contaminants or loosely adhered materials. For concrete substrates, a minimum surface profile of a CSP-3 or higher is required depending on overall substrate conditions and coating requirements. Concrete and other porous or absorptive substrates should be **(SSD) saturated surface dry** with no standing water at the time of the MPC application to the substrate.

• Mixing

MPC must be mixed mechanically using a low-speed drill with a "Jiffy-type" or similar Miracote-approved mixing paddle in a clean mixing container. Pre-mix Liquid Catalyst first to re-disperse any polymer solids that may have settled on the bottom of the pail.

When mixing MPC always pour the liquid catalyst component into the mixing pail first and slowly add the powder component. The mix ratio of powder to liquid may be slightly modified depending on whether a slurry or trowel-grade consistency is desired. Thoroughly mix the MPC until a uniform smooth consistency is achieved that is free of lumps and pockets of dry powder.

OVERVIEW OF INSTALLATION STEPS (Continued)

• Application

Miracote MPC can be applied using a roller, brush, broom, trowel, magic trowel, squeegee or spray equipment. Apply MPC only on properly prepared substrates, and be sure that all voids and bug holes are properly filled by working material into the substrate.

LIMITATIONS

- May reflect moving cracks and control joints. Implement detail as per current published installation guidelines (IG's).
- Staining, streaking and efflorescence may occur when fresh coating is exposed to excessive ponding or running water.
- Prevent any contact with aluminum which can cause an adverse reaction due to MPC's cementitious content.

LIMITED WARRANTY

NO WARRANTY SHALL BE EFFECTIVE UNTIL THE TERMS AND CONDITIONS OF SALE SET FORTH IN CROSSFIELD PRODUCTS CORP. INVOICES ARE MET.

Crossfield Products Corp. warrants to the purchaser of its products that such products are free from manufacturing defect. Crossfield does not warrant or guarantee the workmanship performed by any person or firm installing its products. Crossfield's obligation under this warranty is limited solely to the original purchaser and solely to the remedy of replacement in kind of any product which Crossfield sold which may prove defective in manufacture within one year from date of installation, provided said product was stored correctly and installed within the product's shelf life, by the original purchaser and which Crossfield's examination shall disclose to Crossfield's satisfaction to be thus defective.

IN NO EVENT SHALL CROSSFIELD PRODUCTS CORP. BE LIABLE FOR ANY INCIDENTAL OR CONSEQUENTIAL DAMAGES. THIS WARRANTY IS EXPRESSLY GIVEN IN LIEU OF ALL OTHER WARRANTIES EXPRESSED OR IMPLIED, INCLUDING THE WARRANTIES OF MERCHANTABILITY AND FITNESS FOR USE AND ALL OTHER OBLIGATIONS OR LIABILITIES ON CROSSFIELD'S PART, AND WE NEITHER ASSUME NOR AUTHORIZE ANY PERSON OR PERSONS TO ASSUME FOR US ANY OTHER LIABILITY IN CONNECTION WITH SALE OF A CROSSFIELD PRODUCT. THIS WARRANTY SHALL NOT APPLY TO ANY OF CROSSFIELD'S PRODUCTS, WHICH HAVE BEEN SUBJECT TO ADULTERATION, ALTERATION ABUSE OR MISUSE. CROSSFIELD PRODUCTS CORP. MAKES NO WARRANTY WHATSOEVER IN RESPECT TO ACCESSORIES, PARTS OR MATERIAL NOT SUPPLIED BY CROSSFIELD PRODUCTS CORP., WHICH ARE USED IN CONNECTION WITH ITS PRODUCTS. THE TERM "ORIGINAL PURCHASER" IN THIS WARRANTY MEANS THAT PERSON, CORPORATION OR ENTITY TO WHOM CROSSFIELD PRODUCTS CORP. SOLD ITS PRODUCTS. ANY ACTION TO ENFORCE ANY WARRANTY OR FOR BREACH OF CONTRACT OR ARISING OUT OF ANY CLAIM AGAINST CROSSFIELD PRODUCTS CORP. SHALL BE COMMENCED AND MAINTAINED ONLY IN A COURT OF COMPETENT JURISDICTION IN THE CONTINENTAL UNITED STATES OF AMERICA. THE PURCHASER ACCEPTS THESE TERMS AND CONDITIONS, AND HEREBY EXPRESSLY WAIVES ANY CLAIM TO ADDITIONAL DAMAGES.

CAUTION: ALWAYS KEEP OUT OF THE REACH OF CHILDREN.



Miracote Product Line
Crossfield Products Corp

www.miracote.com

East Coast Office
140 Valley Road
Roselle Park, NJ 07204
P: (908) 245-2808
F: (908) 245-0659

West Coast Office
3000 E. Harcourt Street
Rancho Dominguez, CA 90221
P: (310) 631-6594
F: (310) 886-9119

שייווק בלעדי:



טכנולוגיית (1992) בע"מ

תצוגה ומכירות: הגדר 14, מרכז עינג (ישפרו) מודיעין
מען למכתבים: נהל בוקק 6, מודיעין 7173541
טלפון: 972-8-9702384 פקס: 972-8-9702385
דוא"ל: contact@frp.co.il אתר: www.frp.co.il

MIR.011
MIRACOTE MPC PARK DECK
07-06-2012